

Maintenance and Service Aids

Technical Data Sheet

ELECTROLUBE
THE SOLUTIONS PEOPLE

Page 1

SCP Silver Conductive Paint

SCP provides a thin, smooth, adherent, flexible film of high electrical conductivity that can be applied on a variety of substrates, including plastics, paper, wood, textiles, glass, ceramics and metals. It can be applied by brushing, spraying, dipping, or a pencil and dries quickly at room temperature. SCP is suitable for PCB design and repair, mark sensing e.g. on recording tapes, screening plastic housings against high frequency fields, earthing strips, connections to non-solderable surfaces, electroplating pre-coats, contact surfaces, potentiometer tracks, etc.

- Thin film only required; economic in use
- Good electrical conductivity and low surface resistivity
- Excellent adhesion to wide range of materials
- Cures at room temperature

Typical Properties

Appearance	Grey Liquid
Silver content	45%
Carrier	Solvent Blend
Viscosity @ 25°C	70 mPa s
Density @ 20°C	1.44 g/ml
Surface Resistance @ 0.6 to 2 g/100cm ²	0.01 to 0.03 Ohms/sq
Electrical Rating	0.1 to 1 W/cm ²
Drying time @ 20°C	10 minutes
Temperature Range	-80°C to +125°C
Flash Point	12°C

Description

Silver Conductive Paint

Packaging

3g Bottle
26g Bottle
50g Bottle
1kg bulk

Order Code

SCP03B
SCP26G
SCP50G
SCP01K

Shelf Life

24 months
24 months
24 months
24 months

Directions for Use

Shake or stir the product thoroughly before use. Ensure surface to be coated is clean, dry and free from oil, grease or dirt. Replace cap securely after use to avoid evaporation of the solvents. Use Electrolube CPL after application to prevent oxidation or formation of silver compounds and to prevent mechanical damage.

Revision 2: Aug 2015

Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way,
Ashby de la Zouch,
Leicestershire LE65 1JR
T +44 (0)1530 419 600
F +44 (0)1530 416 640
BS EN ISO 9001:2008
Certificate No. FM 32082